



HIGH PERFORMANCE VpCI® PACKAGING

CorShield® VpCI®-146 Reinforced Paper powered by Nano VpCI® - Corrosion Inhibiting Paper



PRODUCT DESCRIPTION

CorShield® VpCI®-146 Reinforced Paper is the premium corrosion inhibiting reinforced paper in the industry. Our patented Vapor phase Corrosion Inhibiting technology has revolutionized the way metals are protected in an enclosed package. CorShield® VpCI®-146 Reinforced Paper provides superior corrosion protection for both ferrous and non-ferrous metals. CorShield® VpCI®-146 Reinforced Paper eliminates the need to stock a variety of papers for all the different types of metals and alloys you need to protect. Additionally, CorShield® VpCI®-146 Reinforced Paper is non-toxic and doesn't contain any nitrites, phosphates, silicates or other hazardous compounds.

CorShield® VpCI®-146 Reinforced Paper is made from the highest quality neutral natural kraft paper and has excellent tear resistance. There are no chemical concentrations to calculate, no chemical tanks or application system to maintain. Just wrap your products in the paper, and fold edges together. Use adhesive tape as needed to hold paper folds in place. The VpCI® coating on the paper vaporizes, reaching all metal surfaces to provide complete corrosion protection. The unique inhibiting action of the VpCI® forms a very thin and very effective protective layer that does not alter the appearance of products or require removal.

Parts protected with CorShield® VpCI®-146 Reinforced Paper can

be painted, welded, and soldered. The protective layer does not influence physical properties of most sensitive electrical components, including conductivity and resistance.

TYPICAL APPLICATIONS

CorShield® VpCI®-146 Reinforced Paper can be used to protect products for storage and shipment in a wide variety of ways: wrap for single item packaging or interleaving; end closures for shipping tubes; insert strips for recessed areas in large packages; and as sheet liners or separators between products. CorShield® VpCI®-146 Reinforced Paper is used in packaging of metals with pointed, odd shapes or sharp edges where puncture would be an issue with non-reinforced papers. It's also used in applications where damage to the item caused during shipping is a concern when using non-reinforced papers.

The typical applications are:

- Metals industry: coils, wire reels, plate, bar, etc.
- Metal forging and die casting: raw and machined forgings and castings.
- Metalworking: stamping, sheet metal work, springs, bearings, fasteners, tube, pipe, nails, etc.
- Finished products: engines, machinery, tools, hardware, appliances, instruments, motors, etc.
- Electrical and electronic components, controls, etc.

FEATURES

- Extremely durable paper allows you to ignore normal handling issues found in non-reinforced packaging papers.
- One product for all ferrous and non-ferrous metals.
- Non-toxic. Contains no nitrites, phosphates, silicones, chromates or other heavy metals.
- Effective against aggressive environments including humidity, SO₂, H₂S and galvanic corrosion from dissimilar metals.
- Conforms to military specifications MIL-P-3420E.
- Protective layer does not need to be removed prior to further surface finishing or coating application.



- Protects dry or oiled metals during storage, transit and overseas shipment.
- Natural grade paper eliminates package contamination.
- Combines corrosion protection and packaging into one step.

METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Galvanized Steel
- Cast Iron
- Aluminum Alloys
- Copper
- Brass ($\leq 30\%$ Zn)
- Solder

METHOD OF APPLICATION

Products should be packaged as soon after cleaning as possible, but completely dried of residual water. Keep the VpCI® paper as close to the surface of the product as practical, leaving no barrier between the VpCI® paper and the metal surface to be protected.

Standard Construction: Fiberglass reinforced polycoated neutral natural kraft paper, coated with VpCI® material.

TYPICAL PROPERTIES

Property	TAPPI Method	UNIT	CorShield® VpCI®-146 Reinforced Paper
Basis Weight lbs	T-410	lbs/3000ft ² (g/m ²)	90 ± 5 (146 ± 8 g/m ²)
Caliper (thickness)	T-411	Mils (μm)	9 ± 1 (230 ± 25) 13 ± 2 (325 ± 50) at Reinforcing Fiber

STANDARD TEST METHODS

TAPPI T-410	Basis Weight
TAPPI T-411	Caliper
ASTM D 3420-95B	Impact Puncture
ASTM D-1922-94A	Tear Test
MIL-PRF-3420H	Commercial Equivalent to Standard

TECHNICAL PRODUCT INFORMATION

Test Name	Test Method	Parameter	Spec	Value	Unit
Composition	ISO 2286-2	Kraftliner Fabric HDPE film PE		100 13 10 18	gr/m ² gr/m ² gr/m ² gr/m ²
Water Vapor Barrier (WVTR)				0.47	g/hour*m ²

TEST CERTIFICATE

Test Name	Test Method	Parameter	Spec	Value	Unit
Width	ISO 2286-1	Width		2500	mm
Tensile Strength	ISO 1421	Elongation CD Strength CD Elongation MD Strength MD		6,9 260 3,4 642	% N/50mm % N/50mm
Tear Strength	ISO 6383-1	Tear Strength CD Tear Strength MD		14,7 9,51	N/50mm N/50mm
Mass per unit area	ISO 2286-2	Mass per unit area		145	gr/m ²

PACKAGING AND STORAGE

Standard roll size: 100" wide by 350 ft. length (2.5 m x 105 m). Roll weight: 106 lbs (48 kg). Pallet size: 5 rolls across by 4 high, 20 rolls per pallet. Custom sizes, constructions and printing available upon request.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.
BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
<http://www.cortecvci.com>

Printed on recycled paper  100% post consumer

Revised: 12/02/16. Supersedes: 08/22/16. ©Cortec Corporation 2002-2016 of Cortec Corporation.
All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2016, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE INFORMATION

Distributed by: